



Heavy Density HCFC Free Rigid Phenolic Insulation

DENSITY*	ASTM D 1622	lb/ft ³	3.75	5.0	7.5
COLOR			cream	pink	white
K FACTOR*	ASTM C 518	Btu-in./ft ² ·°F	0.19	0.21	0.23
TEMPERATURE LIMIT		°F	-290 °F to + 250 °F	-290 °F to + 250 °F	-290 °F to + 250 °F
COMPRESSIVE STRENGTH	ASTM D 1621	psi			
- Parallel to rise*			58	90	150
- Perpendicular to rise*			43	70	110
TENSILE STRENGTH	ASTM D 1623	psi			
- Parallel to rise*			54	85	130
- Perpendicular to rise*			41	65	100
CLOSED CELL CONTENT	ASTM D 2856	%	>92	>92	>92
WATER ABSORPTION	ASTM C 209	% by volume	.5%	.5%	.5%
FIRE TEST CLASSIFICATIONS	ASTM E 84 25/50 flame and smoke - up to 3 inches thick Meets the requirements of ULC Canada S102 & S127 tests				

*all properties can vary by +/- 5%

OTHER DENSITIES ARE AVAILABLE ON REQUEST PLEASE CONTACT OUR TECHNICAL DEPARTMENT

Insul-phen meets the requirements of ASTM C1126 Type 11 and 111 grade 1 standard specification for faced or unfaced rigid cellular phenolic thermal insulation.

Other information

This information is furnished without warranty, expressed or implied, except that it is accurate to the best knowledge of Resolco Inc. The data on this sheet related only to the specific material designated herein. Resolco Inc. assumes no legal responsibility for use or reliance upon this data. For information regarding specific applications of the product please contact Resolco Inc.

(July 2010)

